



PRODUCT DESCRIPTION		
Color Index	Pigment Blue 15:3	
C.I. No.	74160	
Chemical Type	Cu-Phthalocyanine Blue, beta-mod	
CAS No.	147-14-8	
Hue Angle	240.0	
1/3 ISD Reduction Ratio	1:16.5	DIN EN ISO 53235
1/25 ISD Reduction Ratio	1:144.0	DIN EN ISO 53235

PHYSICAL DATA		
Appearance	Blue Powder	
Density [g/cm ³]	1.6	DIN EN ISO 787-10
Bulk Volume [ltr/kg]	3.8	DIN 53194
Specific Surface [m ² /g]	54	DIN EN ISO 66132
Oil Absorption [ml/100g]	42	DIN EN ISO 787-5

FASTNESS PROPERTIES			
Acid	5	DIN EN ISO 787-4	
Alkali	5	DIN EN ISO 787-4	
Overpainting	5	1)	
Water	5	DIN EN ISO 2836	
Butanol	5	DIN EN ISO 2836	
Butyl Acetate	5	DIN EN ISO 2836	
Xylene	5	DIN EN ISO 2836	
MEK	5	DIN EN ISO 2836	
White Spirits	5	DIN EN ISO 2836	
Heat Resistance [°C]	200	2)	
Light Fastness	DIN EN ISO 105-B01		
Full Shade	8		
1:1 TiO ₂	8		
1/3 ISD	8		
Weather Fastness	DIN EN ISO 20105-A02		
Full Shade	[12 months] 5	[24 months] 5	
1:1 TiO ₂	[12 months] 5	[24 months] 5	
1/3 ISD	[12 months] 5	[24 months] 5	

1) Pigments were tested in an alkyd/melamine system with 30 minutes baking time at 160°C.

2) Pigments were tested in an alkyd/melamine system.
Temperature >200°C DE ≤ 2



APPLICATION PROFILE	
Waterborne Paints	recommended
Air Drying Alkyds	recommended
Stoving Enamels	recommended
Acid Curing Systems	recommended
Amine Curing Epoxies	recommended
Isocyanate Cured Systems	recommended
Powder Coatings	recommended

REGULATIONS	
Germany BfR recom. IX	compliant
APME AP 89/1	compliant
USA (FDA) 21 CFR § 178.3297	listed
Toys Europe EN 71-3	compliant
Toys USA ASTM F 94/62	compliant
CONEG, EC 94/62	compliant
ROHS, 2002/95/E, 2005/618/EC	compliant
End of Life Vehicles, 2000/53/EC, 2002/525/EC	compliant

STANDARD PACKAGING
- 15kg Paper Bags
- Different types of packaging are available on request