



PRODUCT DESCRIPTION		
Color Index	Pigment Red 254	
C.I. No.	56110	
Chemical Type	Diketopyrrolo-Pyrrole	
CAS No.	84632-65-5	
Hue Angle	17.7	DIN EN ISO 53235

PHYSICAL DATA		
Appearance	Red Powder	
Density [g/cm ³]	1.54	DIN EN ISO 787-10
Bulk Volume [ltr/Kg]	2.22	DIN 53194
Specific Surface [m ² /g]	23.2	DIN EN ISO 66132

FASTNESS PROPERTIES		
Acid	5	DIN EN ISO 787-4
Alkali	5	DIN EN ISO 787-4
Water	5	DIN EN ISO 2836
Ethanol	5	DIN EN ISO 2836
Ethyl Acetate	5	DIN EN ISO 2836
MEK	4 - 5	DIN EN ISO 2836
Toluene	4	DIN EN ISO 2836
DOP	5	DIN EN ISO 2836
Paraffin	5	DIN 16524-31965
Butter	5	DIN 16524-31965
Soap	5	DIN 16524-31965
Light Fastness 1/3 SD (print)	7	DIN EN ISO 105-B01
Light Fastness 1/25 SD (print)	6 - 7	DIN EN ISO 105-B01
Heat Resistance [°C]	200	

STANDARD PACKAGING	
- 25kg Paper Bags, 25kg Cardboard Boxes	
- Different types of packaging are available on request	



APPLICATION PROFILE	
Offset	recommended
Publication Gravure	-
Gravure / Flexo, solventborne	recommended
Gravure / Flexo, waterborne	recommended
Decorative Laminates	recommended

REGULATIONS	
Germany BfR recom. IX	compliant
APME AP 89/1	compliant
USA (FDA) 21 CFR § 178.3297	listed
Toys Europe EN 71-3	compliant
Toys USA ASTM F 94/62	compliant
CONEG, EC 94/62	compliant
ROHS, 2002/95/E, 2005/618/EC	compliant
End of Life Vehicles, 2000/53/EC, 2002/525/EC	compliant

® = Registered trademark of Heubach Colour Pvt. Ltd. Our product specifications and application information are based on our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and us.