

PRODUCT DESCRIPTION	
Product	Synthetic Hydrotalcite
Chemical Description	Magnesium Aluminum Hydroxide Carbonate
Chemical Formula	$Mg_{1-x}Al_x(OH)_2(CO_3)_x \cdot 2mH_2O (0 < x \leq 0.5)$
CAS No	110097-59-9
EC No	234-319-3


TECHNICAL DATA		
Appearance	Fine White Powder	
Density [g/cm ³]	2.0	DIN EN ISO 787-10
Specific Surface [m ² /g]	5 - 15	BET
pH (5%)	8 - 9.5	5% Ethanol in Water
Oil Absorption [ml/100g]	35 - 45	DIN EN ISO 787-5
Loss on ignition (%)	43.5 - 45.0	@ 800°C / 4 Hrs.
Loss on Drying (%)	< 0.5	@ 105°C / 4 Hrs.
Al ₂ O ₃ (%)	19 - 23	By titration
MgO (%)	30 - 35	By titration
Particle Size (µm)	80% < 1, 100% < 5	Laser Diffraction

REGULATIONS	
Germany BfR recom. IX	Compliant
APME AP 89/1	Compliant
USA (FDA) GRAS	Listed
Food Contact Materials (EU)	PM/REF No.34690
Toys Europe EN 71-3	Compliant
Toys USA ASTM F 94/62	Compliant
CONEG, EC 94/62	Compliant
ROHS, 2002/95/E, 2005/618/EC	Compliant
End of Life Vehicles, 2000/53/EC, 2002/525/EC	Compliant


PACKAGING
- 25kg LDPE Bags with inside liner
- Different types of packaging are available on request

APPLICATION & ADVANTAGES
HISORB 4A acts as excellent halogen scavenger, stabilizer for polyolefines produced with Ziegler-Natta, Friedel Crafts or other acid catalysts and acid acceptor for EVA, halogenated rubber etc. HISORB 4A is having following advantages.
<ul style="list-style-type: none"> ● Safe (Approved for food contact) ● Non-Kosher/Non -Halal offending coatings available ● Efficient (Applications require only small dosages) ● Polymer yellowing is suppressed ● No stearic vapour problem ● Reduction of water carry -over ● High anti-corrosivity ● Negligible impact on mechanical strength

ELECTRON MICROGRAPH



PARTICLE SIZE DISTRIBUTION



® = Registered trademark of Heubach Colour Pvt. Ltd. Our product specifications and application information are based on our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and us.